

GTS-65

Global Transmission Sleeve

The GTS-65 system provides superior corrosion protection and excellent bonding on pipelines operating up to 65°C. GTS-65 has been designed with a unique adhesive technology that remains “open” longer than traditional adhesives. Also, special surface active agents allow bonding to lower surface energy coatings (such as polypropylene). As a result, lower preheat temperatures are required to attain true adhesive wet-out and superior bonding to PE, PP and FBE surfaces is achieved.

Superior Force Cured Epoxy

- Proven method of force curing the liquid epoxy to the steel allows the installer to “pre-inspect” the joint prior to sleeve application
- Force cured epoxy cannot be displaced during the aligning and shrinking stages of the sleeve installation

Unique Adhesive Technology

- Allows for lower installation pre-heat temperatures and superior bonding to PE, PP and FBE coatings
- Adhesive has been formulated to bond directly to the main line coating; epoxy is applied to the steel only

Flexible Installation

- GTS-65 can be used as either a 2-layer or 3-layer sleeve system with the same low pre-heat temperature
- For added flexibility, the sleeve can be supplied as bulk rolls or pre-cut to the required pipe size

Long Term Corrosion Protection

- Provides a protective coating with the structural integrity of a seamless tube, providing excellent resistance to cathodic disbondment and excellent durability against abrasion and chemical attack

Saves Time & Money

- Lower pre-heat means less time heating



Applications



Oil & Gas



Offshore Pipelines



Onshore Pipelines



GTS-65

Global Transmission Sleeve

Sleeve Operating Characteristics	Test Method	Typical Values	
Pipeline Operating Temp.		Up to 65°C (150°F)*	
Minimum Installation Temp.		90°C (195°F)	
Main Line Coating Compatibility		PE, HPPC, PP, FBE	
Adhesive Properties			
Softening Point	ASTM E28	94°C	
Lap Shear @ 23°C	ISO 21809-3	245 N/cm ²	
Lap Shear @ 60°C	ISO 21809-3	8 N/cm ²	
Backing Properties			
Tensile Strength	ASTM D638	24 MPa	
Elongation	ASTM D638	600%	
Hardness	ASTM D2240	55 Shore D	
Volume Resistivity	ASTM D257	10 ¹⁷ ohm-cm	
Sleeve Properties			
Adhesion Strength @ 23°C	ISO 21809-3	>70 N/cm	
Impact Resistance	ISO 21809-3	>15 J	
Indentation Resistance	ISO 21809-3	0.65 mm (pass)	
Cathodic Disbondment @ 23°C, 28 days	ASTM G8	3 mm rad†	
Low Temp. Flexibility	ASTM D2671-C	>-32°C	
Thickness	T	L	S
Backing (nominal thickness as supplied)	0.9 mm (0.035")	0.9 mm (0.035")	1.1 mm (0.045")
Adhesive (nominal thickness as supplied)	0.9 mm (0.035")	1.3 mm (0.050")	1.5 mm (0.060")

* Actual temperature rating is dependant on specific project requirements and conditions.

† As a 3-layer system

Epoxy usage can be referenced on the Liquid Epoxy Product Data Sheet.

Since 1967, Canusa-CPS has been a leading developer and manufacturer of specialty pipeline coatings for the sealing and corrosion protection of pipeline joints and other substrates. Canusa-CPS high performance products are manufactured to the highest quality standards and are available in a number of configurations to accommodate many specific project applications.

The product information shown here is intended as a guide for standard products.

Consult your Canusa representative for specific projects or unique applications.



Canusa-CPS A division of Shawcor Ltd.

Head Office

25 Bethridge Road
Toronto, ON, Canada M9W 1M7
Tel: +1 416 743 7111
Fax: +1 416 743 5927

Canada

Dome Tower St. 2200, 333-7th Avenue SW
Calgary, AB, Canada T2P 2Z1
Tel: +1 403 218 8207
Fax: +1 403 264 3649

Americas

5875 N. Sam Houston Pkwy W., Suite 200
Houston, TX, USA 77086
Tel: +1 281 886 2350
Fax: +1 281 886 2353

Middle East

ADPC - Mussafah Port, P.O. Box 2621
Abu Dhabi, UAE
Tel: +971 2 496 3500
Fax: +971 2 496 3501

Europe, Africa & Russia

Dellaertweg 9-E, Gebouw "Le Carrefour"
2316 WZ Leiden, The Netherlands (NL)
Tel: +31 71 80 802 70
Fax: +31 71 80 802 71

Asia-Pacific

101 Thomson Road, #11-03 United Square
307591 Singapore
Tel: +65 6749 8918
Fax: +65 6749 8919

Quality Management system registered to ISO 9001

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the product data sheet when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this data sheet is to be used as a guide and is subject to change without notice. This data sheet supersedes all previous data sheets on this product. E&OE

PDS_GTS65_rev019